

# Horizontally Perforated Brick No200



UNITS /  
PALETTE:  
**105**

 **EPD**<sup>®</sup>  
THE INTERNATIONAL EPD<sup>®</sup> SYSTEM

 **EPD**<sup>®</sup>  
CLIMATE DECLARATION



Horizontally Perforated Clay Brick, for use in protected masonry, category II, certified according to EN 771-1:2011+A1:2015.

## TECHNICAL DATA

Dimensions (LxWxH) (mm)	330x200x150
Weight per Unit (kg/unit)	7,10
Masonry Thickness (mm)	200
Units/m <sup>2</sup>	18
Estimated Masonry Weight (kg/m <sup>2</sup> ) without mortar	127,80
Gross Dry Density (kg/m <sup>3</sup> )	725
Net Dry Density (kg/m <sup>3</sup> )	1.900
Mean Compressive Strength (perpendicular to bed face) (N/mm <sup>2</sup> )	≥ 3,0
Water Vapour Permeability $\mu$	5 / 10
Durability against freeze/thaw	F0
Reaction to Fire	A1