

# ORTHOBLOCK K120



UNITS /  
PALETTE:  
**96**

**EPD**<sup>®</sup>  
THE INTERNATIONAL EPD<sup>®</sup> SYSTEM

**EPD**<sup>®</sup>  
CLIMATE DECLARATION



Vertically Perforated Clay Brick, for use in protected masonry, Category II, certified according to EN 771-1:2011+A1:2015.

## TECHNICAL DATA


Masonry	Non-Load Bearing
Dimensions (LxWxH) (mm)	380x120x240
Weight per Unit (kg/unit)	8,85
Masonry Thickness (mm)	120
Units/m <sup>2</sup>	11
Estimated Masonry Weight (kg/m <sup>2</sup> ) without mortar	97,35
Gross Dry Density (kg/m <sup>3</sup> )	870
Net Dry Density (kg/m <sup>3</sup> )	1.900
Mean Compressive Strength (perpendicular to bed face) (N/mm <sup>2</sup> )	12,0
Thermal Conductivity Coefficient $\lambda_{10,dry,unit}$ (W/mK)	0,2172
Sound Reduction Index $R_w$ (dB)	43 **
Water Vapour Permeability $\mu$	5 / 10
Durability against freeze/thaw	F0
Reaction to Fire	A1

## SUPPLEMENTARY PRODUCTS



**BONDING MORTAR  
OPΘOBLOCK BOND**  
(paper bag of 25kg)

Coverage:  
6,0-9,0 m<sup>2</sup> masonry per bag \*



**METAL LINTEL**

Unit's Width: 12cm

\* The above coverage of **OPΘOBLOCK BOND** is indicative and it is the result of laboratory and on site measurements. It includes only horizontal joints 3mm thick (vertical joints in non-load bearing masonries built with **OPΘOBLOCK** are not required).

\*\*Laboratory Measurement