

ORTHOBLOCK[®] PLUS NK250



UNITS /
PALETTE:
64

EPD[®]
THE INTERNATIONAL EPD[®] SYSTEM

EPD[®]
CLIMATE DECLARATION



Vertically Perforated Clay Brick, for use in protected masonry, Category II, certified according to EN 771-1:2011+A1:2015.

TECHNICAL DATA

Masonry	Non-Load Bearing
Dimensions (LxWxH) (mm)	250x250x240
Weight per Unit (kg/unit)	10,65
Masonry Thickness (mm)	250
Units/m ²	16
Estimated Masonry Weight (kg/m ²) without mortar	170,40
Gross Dry Density (kg/m ³)	760
Net Dry Density (kg/m ³)	1.900
Mean Compressive Strength (perpendicular to bed face) (N/mm ²)	9,0
Thermal Conductivity Coefficient $\lambda_{10, dry, unit}$ (W/mK)	0,0856
Thermal Design Conductivity Coefficient $\lambda_{equ, design, masonry}$ (with 3mm ORTHOBLOCK BOND) (W/mK)	0,1004
Thermal Transmittance $U_{w, design}$ without any plaster (with 3mm ORTHOBLOCK BOND) (W/m ² K)	0,3758
Sound Reduction Index R_w (dB)	50 **
Water Vapour Permeability μ	5 / 10
Durability against freeze/thaw	F0
Reaction to Fire	B-S1, d0

* The above coverage of **OPΘOBLOCK BOND** is indicative and it is the result of laboratory and on site measurements. It includes only horizontal joints 3mm thick (vertical joints in non-load bearing masonries built with **OPΘOBLOCK** are not required).


** Calculated Measurement

SUPPLEMENTARY PRODUCTS



**BONDING MORTAR
OPΘOBLOCK BOND**
(paper bag of 25kg)

Coverage:
2,5-4,5 m² masonry per bag *



METAL LINTEL

Unit's Width: 25cm